



ZnAl 95

Introduction

ZnAl 95 has good corrosion resistance than either pure Zinc or Aluminum, by combining the advantages of both materials. It is used for corrosion protection in both atmospheric and marine environments.

SURFACE PREPARATION

Surface should be clean, white metal, with no oxides (rust), dirt, grease, or oil on the surface to be coated. Note: It is best not to handle surfaces after cleaning. Recommended method of preparation is, to grit blast with 24 mesh aluminum oxide, rough grind, or rough machine in a lathe.

Application

- Atmospheric corrosion protection
- Electrical conductance on components
- Atmospheric and immersion corrosion protection
- Barriers, posts and poles, offshore structures and marine structures.
- EMI and RF shielding on plastic components (electric arc spray only)

Chemical composition

Type	Chemical composition		
	Zn	Al	Others
Zn Al95	Balance	5	-

Specifications

Grade	AWS
Zn	C2.25/C2.25M W-Zn-1

Physical Properties

Grade	Density	Rockwell Hardness
ZnAl	7.18 g/cm ³	

Typical Deposit Characteristics

Grade	Typical Hardness	Bond Strength	Deposit Rate	Deposit Efficiency	Machilityneab
Zn Al95	HRB 40 –45	20.7 – 24.1 Mpa	/	/	Good

Standard Sizes & Packing

Diameter	Packing	Wire Weight
1/16 (1.6mm)	D 300 Spool	15kg(33 lb)/spool

Other sizes can be produced by customers' requirement.

WISDOM CONSUMABLES

ADD: Room1202 No.1288 Zhennan Rd Shanghai 200331, China

Tel: +862161395047

Fax: +862161395049

E-mail: jim@wisdomsino.com

Website: <http://www.wisdomsurface.com>